

2019-11-01 00:00:00

3M™ Adhesive Transfer Tape 9775WL

Product Description

Finite Element Analysis (FEA) data is available for this product at: [3m.com/FEA](https://www.3m.com/FEA)

3M™ Adhesive Transfer Tape 9775WL with 3M™ Adhesive 300MP is suitable for bonding to most surfaces. The acrylic adhesive provides an excellent bond to various fabricated foams, fabrics, substrates, and has good shear strength at elevated temperatures. This tape also meets the highly variable needs of most gasket fabricators.



Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Physical Properties

Total Tape Thickness		
5 mil	0.005 in	0.127 mm

Property: Total Tape Thickness
Method: ASTM D3652

Property	Values	Test Name
Liner Print	None	
Liner Thickness	7 mil	0.18 mm
Adhesive Type	300MP Acrylic Adhesive	
Liner	96# Polycoated Kraft Paper	
Liner Color	White	Primary

Typical Performance Characteristics

90° Peel Adhesion			Dwell/Cure Time	Dwell Time Units	Temp C	Temp F	Environmental Condition	Backing	Substrate
5.5 lb/in			24	hr	23C	72F	50%RH	5 mil Aluminum Foil	
8 N/cm	72 oz/in	9.8 N/cm	15	min	23C	72F	50%RH	2 mil Aluminum Foil	ABS
5.1 N/cm	46 oz/in		15	min	23C	72F	50%RH	2 mil Aluminum Foil	Polypropylene (PP)
88 oz/in			72	hr	23C	72F	50%RH	2 mil Aluminum Foil	Stainless Steel
19.7 N/cm	177 oz/in		72	hr	70C	158F	50%RH	2 mil Aluminum Foil	Stainless Steel
5.4 N/cm	49 oz/in		72	hr	23C	72F	50%RH	2 mil Aluminum Foil	ABS
4.9 N/cm	44 oz/in		72	hr	23C	72F	50%RH	2 mil Aluminum Foil	Polypropylene (PP)
12.2 N/cm	110 oz/in		72	hr	38C	100F	100%RH	2 mil Aluminum Foil	Stainless Steel

Table continued on next page

Typical Performance Characteristics (continued)

90° Peel Adhesion			Dwell/Cure Time	Dwell Time Units	Temp C	Temp F	Environmental Condition	Backing	Substrate
7.2 N/cm	65 oz/in		72	hr	70C	158F	50%RH	2 mil Aluminum Foil	Polypropylene (PP)
6.1 N/cm	55 oz/in		72	hr	70C	158F	50%RH	2 mil Aluminum Foil	ABS

Property: 90° Peel Adhesion
 Method: ASTM D3330
 notes: 12 in/min (300 mm/min)

Static Shear	Temp C	Temp F	Substrate	Notes	Dwell/Cure Time	Dwell Time Units	Test Condition
10000 g	23C	73F	Stainless Steel	Tested at various temperatures and gram loadings. 0.5 in ² (3.23 cm ²). Will hold listed weight for 10,000 minutes (approximately 7 day).			
10000 min				1" x 1" Overlap	60	min	1000 g @ Room Temperature
10000 min				1" x 1" Overlap	60	min	250 g @ 70°C (158°F) high temperature shears

Property: Static Shear
 Method: ASTM D3654

Property	Values	Test Condition	Method	Test Name	Dwell/Cure Time	Dwell/Cure Units	Temp C	Temp F	Environmental Condition	Substrate	Backing	Notes
Short Term Temperature Resistance	250 °F 121 °C	Short Term										(minutes, hour)
Long Term Temperature Resistance	200 °F 93 °C	Long Term										(day, weeks)

Table continued on next page

Typical Performance Characteristics (continued)

Property	Values	Test Condition	Method	Test Name	Dwell Time	Dwell Time Units	Temp C	Temp F	Environmental Condition	Substrate	Backing	Notes
UV Resistance	Adhesive is resistant to oxidation and ozone when exposed to air or ultraviolet light.											
90° Peel Adhesion Polypropylene (PP)	2.87 lb/in		ASTM D3330	90° Peel Adhesion	72	hr	23C	72F	50%RH	Polypropylene (PP)	Pyralis PET	12 in/min (300 mm/min)
90° Peel Adhesion ABS	4.5 lb/in		ASTM D3330	90° Peel Adhesion	72	hr	23C	72F	50%RH	HABS		

Available Sizes

Property	Values	
Standard Roll Length	180 yd	
Maximum Available Width	60 in	
Normal Slitting Tolerance	± 1/32 in	
Core Size (ID)	75 mm	3 in

Typical Environmental Performance

Humidity Resistance

No adverse effect on the bond after exposure to 100% relative humidity at 100°F (38°C)

Storage and Shelf Life

Store in the original packaging at room temperature conditions of 72°F (22°C) and 50% relative humidity. Keep out of direct sunlight. Product retains its performance properties for 24 months from date of manufacture.

Industry Specifications

EN 45545 test report for details (ISO 5659-2, ISO 9239-1, ISO 5658-2, ISO 5660-1)

Trademarks

3M is a trademark of 3M Company.

References

Property	Values
3m.com Product Page	https://www.3m.com/3M/en_US/company-us/all-3m-products/~/3M-Adhesive-Transfer-Tape-9775WL/?N=5002385+3293240967&rt=rud
Safety Data Sheet SDS	https://www.3m.com/3M/en_US/company-us/SDS-search/results/?gsaAction=msdsSRA&msdsLocale=en_US&co=ptn&q=9775WL

Family Group

	9772WL	9773WL	9774WL	9775WL
Long Term Temperature Resistance (°F) Test Condition: Long Term (day, weeks)	200	200	200	200
Short Term Temperature Resistance (°C) Test Condition: Short Term (minutes, hour)	121.1111	121.1111	121.1111	121.1111
Liner Color Test Name: Primary	White	White	White	White
Long Term Temperature Resistance (°C) Test Condition: Long Term (day, weeks)	93.33333	93.33333	93.33333	93.33333
Total Tape Thickness (mm)	0.0508	0.0762	0.1016	0.127
Adhesive Type	300MP Acrylic Adhesive	300MP Acrylic Adhesive	300MP Acrylic Adhesive	300MP Acrylic Adhesive
Liner	96# Polycoated Kraft Paper			
Liner Thickness (mm)	0.18	0.18	0.18	0.18

ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

Disclaimer: 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use. Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit www.3M.com.



3M United States
3M Center
St. Paul, MN 55144-1000
800-362-3550
www.3M.com

Please recycle.
© 3M 2021. All Rights Reserved.

The brands listed above are trademarks of 3M

